

Total Petrochemicals Polypropylene 4624WZ is a nucleated impact copolymer with a Melt Flow of 15 g/10min., combining good fluidity and mechanical properties.

4624WZ is characterized by significantly improved impact resistance and mold release while maintaining excellent antistatic properties, good processability.

4624WZ has been developed specifically for the injection molding pales and crates requiring extra toughness.

<u>Resin Properties</u>	<u>Typical Value</u>	<u>Test Method</u>
Melt Flow, g/10 min.	15	ASTM D-1238
Density , g/cm ³	0.905	ASTM D-1505
Melting Range, °C	160 - 165	TOTAL Method
<u>Mechanical Properties</u>		
Tensile Strength at Yield, psi (M Pa)	3800 (27)	ASTM D-638
Elongation at Yield, %	7	ASTM D-638
Flexural Modulus, psi (M Pa)	160,000 (1,100)	ASTM D-790
Izod Impact (Notched)		
@ 23°C, ft-lb/in (J/m)	3.5 (190)	ASTM D-256
Charpy Impact Strength		
@ 23°C, kJ/m ²	13.5	DIN 53453
<u>Thermal Properties</u>		
Vicat Softening Point, °C	148	ASTM D-1525
Heat Deflection Temperature, °C	90	ASTM D-648

4624WZ 05/2012

Corporate Office USA
P.O. Box 674411
Houston, TX 77267-4411
800.344.3462
www.totalpetrochemicalsusa.com

Technical Center
P.O. Box 1200
Deer Park, TX 77536
281.884.7500

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TOTAL products must be guided by the users own methods for selection of proper formulation. TOTAL PETROCHEMICALS USA, INC. disclaims any responsibility for misuse or miss application of its products. TOTAL MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TOTAL'S liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.